


HOMOGENEOUS  
COMPACT VINYL

# Specjal 43 Plus

CERTIFICATION & CLASSIFICATION		STANDARDS	Specjal 43 Plus
<b>Classification</b>	ISO 10874 – EN 685		Commercial: 34 Industrial: 43
<b>Type of floor covering</b>	ISO 10581		Homogeneous vinyl flooring. Type II.
<b>ISO certification</b>			Jaslo ISO 9001, Jaslo ISO 14001
TECHNICAL CHARACTERISTICS		STANDARDS	Specjal 43 Plus
<b>Total thickness</b>	ISO 24346 – EN 428		2.0 mm
<b>Wear layer thickness</b>	ISO 24340 – EN 429		2.0 mm
<b>Total weight/m<sup>2</sup></b>	ISO 23997 – EN 430		3500 g
<b>Surface treatment</b>			PUR
TECHNICAL PERFORMANCES		STANDARDS	Specjal 43 Plus
<b>Residual indentation</b>	ISO 24343-1 – EN 433		≤ 0.1 mm
<b>Reaction to fire</b>	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2		Class B <sub>f1</sub> s1 ≥ 8 kW/m <sup>2</sup> Pass
<b>Dimensional stability</b>	ISO 23999 – EN 434		≤ 0.40 % for rolls ≤ 0.25 % for tiles
<b>Flexibility</b>	ISO 24344, Method A		No cracking on 20 mm mandrel
<b>Castor chair test</b>	ISO 4918 – EN 425		Suitable
<b>Marine certificate</b>	IMO Res. MSC. 307(88) IMO (2010 FTPC) Annex 1, Part 5 and 2		MED 1650284 SAS F160364
<b>Antistatic properties</b>	EN 1815		≤ 2 kV
<b>Electrical resistance</b>	EN 1081		R <sub>1</sub> ≤ 10 <sup>9</sup> Ω
<b>Light fastness</b>	EN ISO 105-B02		≥ level 6
<b>Chemical resistance</b>	ISO 26987 – EN 423		Good resistance
<b>Bacteria resistance</b>	ISO 846: Part C		Does not favour growth
<b>Slip resistance</b>	DIN 51130 EN 13893		R9 ≥ 0.3
<b>Seam strength</b>	EN 684		Average value: ≥ 240 N/50 mm Individual values: ≥ 180 N/50 mm
<b>Underfloor heating</b>			Suitable – max 27°C
<b>Form of delivery</b>	ISO 24341 – EN 426 Sheet (rolls)		20 running meters x 200 cm
<b>Colours</b>			16

The above information is subject to modification for the benefit of further improvement (05/2017).